
Kiln Glass







Transparent Sheet Glass COE 90







Opaque Sheet Glass COE 90







90-14 Orange Red





Wissmach Opaque 90 Tower by Petra Kaiser



Prisma

Prisma is our fusing line of mixed colors. Primarily a mix of 2 colors and sometimes 3, which can result in some additional color hues. Mixing color is a manual process and each piece will be different. Some are so interesting that you might just want to use it as a whole piece to create something beautiful.





90-18 Black/Crystal



90-22 Yellow tr./Crystal



90-19 Red tr./Crystal



90-23 White 75%/Crystal



90-20 Red tr./Yellow tr.



90-24 Blue tr./Crystal



90-21 Yellow tr./White



90-25 Green tr./Crystal







Bright Blue tr./White



90-28 Red tr./White



90-31 White/Blue tr./Red tr.



90-34 White 50%/Crystal



90-27 Green tr./Blue tr.



90-29 Blue tr./White



90-32 Bright Green tr./White



90-35 Crystal/White 25%

*tr. stands for transparent

*tr. stands for transparent



All of our colors are available with our Luminescent coating.


Our coated glass is similar to the iridescent coatings, but not quite the same. Therefore, we call it luminescent.

You can achieve different effects when firing with the coated side up or down. It is ideal for reversed fusing projects and sculptures which you want to look their best from both sides.

Luminescent Glass Tutorial

Please visit: Wissmachglass.com/FreeTutorials

Luminescent coated glass - coated side fired down!



Below you see a few sample tiles to give you an idea of the color. All tiles were fused luminescent side towards the kiln shelf.












90-04-LU Light Blue 90-06-LU Champagne 90-11-LU Bright Green



I've been in love with Wissmach luminescent glass since several years. The beautiful sheen is mesmerizing. Everybody wanted one of my pieces! I've given many as gifts. Last fall my Rustic Bowl received the Second Place Ribbon for fused glass art at the Arizona State Fair! Best to You, Gail A. Price

"Putting It All Together" is a workshop taught by Cyndi Seeberger, at Hollander Glass Texas. This Zebra bowl is stunning in real life. The shimmering mottled coating of Wissmach Luminescent glass is like none other."





Luminescent Project!

This small project lesson will give you a head start on using our luminescent glass. You should fire the glass luminescent side towards the kiln shelf or towards the mold. For that reason we developed some reverse fusing molds. Kaiser- Lee Board is a fiber board that is easy to cut and carve and therefore will make ideal long lasting molds for this technique.

Ok, let's have a look at a real project which is named "Ostrich Plate".

Step 1: Choose a mold - in this case we are using a reverse Kaiser Lee Board mold with a pattern created with Papyros Paper. (Yes, you can find it on YouTube).

Step 2: Choose a piece of glass. we used a 96-14 reactive blue, luminescent - 9" x 9" and placed it luminescent side down onto the mold.

Step 3: Cut a piece of 4" x 4" square 96-02 black luminescent and place it luminescent side up on the back of the plate. This will not be seen from the front, just adds a little surprise, when people turn over the plate.

Step 4: To preserve the luminescent coating on the black glass, I added some cut out shapes of Papyros Paper™ which will protect the luminescent where it is placed on the glass.

Step 5: On a Kaiser Lee Board mold you can full fuse and slump in one firing. In our kiln we used the following schedule:



Wissmach luminescent coating is a low fire coating. But with a few tricks you can use it as a beautiful design

First Rule: When you cap the luminescent coating with another piece of glass you will lose it. This can be used as a subtle design element, by capping it partly with shapes of clear glass.

Second Rule: Avoid direct heat to the coated side. Even when you fire the coated side down, hot air could expand between vour kiln

washed shelf/mold and the glass. In most cases it helps when you use a shelf paper between glass and mold/shelf.

Please read through the project lesson and you will understand. We also have a luminescent video on our YouTube channel. Search for "Wissmach glass for your glass art".







600°F (300°C) to 1000°F (540°C) hold :10 **Firing** to 1420°F (770°C) hold :10 to 950°F (510°C) hold 1:00 Schedule! ▶ 100°F (38°C) to 700°F (370°C) hold :00



Textured Sheet Glass!

Normally textures will fire away in the kiln. Most of our textured glass is coated with a metal coating that you know as dichroic coating. But you too can keep the textures with the help of glass paints, enamels or mica paints. Visit our YouTube channel for instructions.

























and fires beauti-




Moss







Sheet Glass Size and Thickness!





Kiln Glass Variety Boxes!

Our Variety Boxes come in 3 sizes and 4 different glass selections. We offer them in all Wissmach 90 and 96 glass colors through our network of distributors.

Boxes in different Sizes	Studio	Instructor	Student
Glass Size	16" x 16"	11" x 11"	8" x 8"
Standard	10 sheets in a variety of colors 10 sheets in luminescent 10 sheets in black, white and clea		
Deluxe			
Basic			
Prisma	10 sheet	lar Prisma	



custom sizes and any size circles.

Call your distributor for Pricing!



Wissmach - Glass - Firing - Suggestions

One Size Fits All - Firing Schedule! ... Wouldn't That Be Nice?



That's only going to happen when all your glass pieces have the I suspected the difference in firing would be the issue and so I same size, shape and color. Never have firing schedules been so slow and hold times so long and when I ask people why, the cracking after firing I decided to talk to you about firing sched-results from my research are explained on the following pages. ules and their consequences. First I tested the glass in question to see if there is any stress between the white and the clear. And each test so far has shown absolutely no stress.

went back to books on glass fusing including my own, wondering if I could find a scientific explanation for all my theories typical answer is: "Somebody gave it to me and it works". After when studying those schedules. After several days of research 2 incidents where people reported the Wissmach white glass I think I found the scientific explanations I was looking for. The

Petra Kaiser, Wissmach Kiln Glass Consultant

Then I tried to copy the piece and see if it would crack. But so far so good - I could not get the glass to crack.

	Segment or Step	Rate (DPH)* (Speed)	Temperature (Destination)	Soak or Hold in Minutes	Reasoning Do not ask HOW, ask WHY and bypass generic firing Schedules!
1	Initial Heat Cycle	600°F 222°C	1000°F 538°C	:10	Be efficient and heat uniformly to avoid thermal shock

In an initial first fuse firing, where all the glass starts out with layers of 3 mm glass, you can go up between 900°F (482°C) and 600°F (222°C) per hour. The speed depends also on the size of glass. Anything under 12" (30 cm) can be easily heated at the rate of 900°F (482°C) and bigger than 12" (30 cm) you can slow it down to 600°F (222°C) per hour.

Let's assume you have already fused a blank and now want to fuse it again, or kiln form it on a mold, you should slow down the initial heat cycle - and depending on size of the piece you can go up 450°F (232°C) and 300°F (148°C) per hour. Re-firing a cast glass piece of 3/4" (2 cm) thickness I do not go slower than 200°F (93°C).

Holding it for 10 minutes at 1000°F (538°C) is sufficient to avoid thermal shock before you advance to the Pre Rapid Heat.

2	Pre Rapid Heat Soak	AFAP***	1210°F 651°C	:15	Optional. No more worries about thermo shock, just equalize temperatures and minimize bubbles.
3	Rapid Heat to Process Temp.	AFAP***	1410°F ** 765°C **	:12	Going up fast will avoid devitrification and in- creases efficiency. Choose the right Process

In this part of the firing you decide about your final result and adjust the Time and Temperature for the process like: tack fuse, full fuse, slump drape, casting, combing Lower temperatures and longer hold times usually will give you better results. Avoid over firing and undesired results, like kiln wash sticking to glass and shifts in color and transparency, bursting bubbles and even shifts in compatibility.

There is a relation between hold time and temperature. You can full fuse glass by holding it for several hours at 1250°F (676°C). So holding it at any stage for an extended amount of time can change the desired results and are unnecessary and inefficient.

Process Temperatures: These are only starting points. Please adjust the process temperatures to your liking and keep firing notes.

Tack Fuse: 1300°F (704°C) Fuse: 1410°F (765°C) Slump: 1280°F (693°C) Drape Over: 1180°F (637°C) Cast: 1440°F (782°C) Combing: 1600°F (871°C)

There is a relation between hold time and temperature. You can full fuse glass by holding it for several hours at 1250°F (676°C). So holding it at any stage for an extended amount of time can change the desired results and are unnecessary and inefficient.


Page 22- 100 - Cookie Cutter Schedules - oops - sorry we will not provide them. With the suggested Process Temperatures for Wissmach glass and our Free e-book online you should be able to write your own.

	Segment or Step	Rate (DPH)* (Speed)	Temperature (Destination)	Soak or Hold in Minutes	Reasoning Do not ask HOW, ask WHY and bypass generic firing Schedules!
4	Rapid Cool to An- neal Soak	AFAP***	900°F 482°C	:45	Rapidly go through the devitrification zone. Equalize internal glass temperature before going through the annealing zone.
		C) difference i			oint where top middle and bottom have no inimum requirement, before the glass keeps
5	Anneal Cool	100°F 38°C	700°F 371°C	:1	Once you are past the strain point the glass will not anneal any more.
	The actual range for the strain point in glass is between 800°F and 880°F. Taking the glass slowly through 700°F is playing it safe.				
6	Final Cool Down	Natural Rate	90°F 32°C		Leave the kiln closed to avoid thermal shock.
			© Copy	right 2017 by	Wissmach Glass & Petra Kaiser, all rights reserved

The complete Firing Suggestions e-book is available for FREE on our website

Wissmachglass.com

10 11



Transparent Sheet Glass COE 96





triangle set up.



Opaque Sheet Glass COE 96

Our opaque glass gets a beautiful shine in the firing process. Please be aware that the colors can strike a darker hue. Therefore, we show each color unfired (left picture) and fired (right

Reactive Glass!

In glass fusing we call glass "reactive" when the metals in one glass react with the metals in another and as a result, create a fine darker line where the two colors meet.

When you combine the colors to the left with the colors on the top row, chances are that you will get some nice reactions.





96-02 Black



96-03 White



96-04 Classic Violet



96-05 Superior Blue

96-06 Pale Green

96-07 Olive Green


96-08 String of Pearls

14

Octopus Vessel by Petra Kaiser








By Petra Kaiser



96-41 Dark Red

96-42 Orange



projects made from 96-39 because it keeps reacting". 96-39 is a Prisma glass,

which is made with 96-08 String of Pearls and 96-14 reactive blue and yes, it will

react even more with each

96-44

96-45

96-14 Reactive Blue



Prisma

Each Prisma combination can come in a variety of color densities as you can see in the following samples.

- 96-28 is White with streaks of Midnight Blue,
- 96-29 is Midnight Blue with streaks of White,
- 96-30 is Midnight Blue with streaks of Crystal.

The first part of the color name is the more dominant color of the Prisma Glass™.



96-33 White/Olive Green



96-34 Olive Green/Blue



Blue tr./Olive Green



Prisma



White/Deep Sky Blue tr.



Crystal/Deep Sky Blue tr.



96-23 White/Superior Blue



96-24 Crystal/Superior Blue



96-36 Black/Pearl



96-37 Reactive Blue/Oyster Pearl



Reactive Blue/Black



96-39 Oyster Pearl/Reactive Blue




96-25 Crystal/Black



96-26 White/Crystal



96-27 Crystal/Reactive Blue



White/Dark Bluet tr.



96-44 Crystal/ Sea Blue tr.




96-45 Sea Blue tr./Crystal



Bear Candle Shelter by Lisa Vogt







Dark Blue tr./White



96-30 Crystal/Dark Blue tr.



96-31 White/Violet



96-32 Olive Green/White



96-48 White/Steel Blue tr.



96-49 Steel Blue tr./White

*tr. stands for transparent


*tr. stands for transparent



Wissmach Glass Frit!











Frit Project

Step 1: Take a few random pieces of clear glass and cover them with a thin layer of frit. I used Aloe Vera for the task.

Step 2: Fire your glass at full fuse temperature.

Step 3: Cut the fired glass on the

back side into 1/4" (1 cm) wide strips.

Step 4: Assemble them on edge to a rectangle by adding several pieces in one row. You can fill in wide gaps with some clear medium size frit.

Step 5: Full fuse again at your favorite full fuse temperature. Mine is $1410\,^{\circ}\,F$ - $765\,^{\circ}\,C$ and hold for $10\,$ minutes.

Step 6: Place it on an angle on a Kaiser Lee Board drape mold and drape it at 1190°F - 645°C - hold 10 minutes.





Mo = Mosaic







Medium (M) - adding texture

Coarse (C) - add sparkly rim to glass for nice luminary drapes.

Mosaic (MO) - use as base layer for casting forms. The thicker your frit grains the less air and the less shrinkage you will have in your form.





Paul Wissmach Glass Company



Paul Wissmach Glass Company manufactures a wide range of colors to please the palette of any artist, architect, or designer - add color mixtures and textures you get more than 3000 possibilities. In over 100 years of glass making we are one of the longest lasting glass companies here in the United States. Most of those years we produced stained glass for cold working techniques.





Making glass is a hot business, both literally and figuratively. The factory has 14 brick furnaces that use natural gas to heat the limestone, soda ash and sand to 2,200°F (1,200°C). Different mixtures of ingredients create the distinct Wissmach colors. After heating, workers scoop the molten glass from the furnace and wheel it over to the glass press where a roller presses it into one of the 19 patterns that the company produces. The glass then travels down a 125 foot conveyor through a temperature controlled kiln called a lehr. The purpose of the lehr is to anneal the glass, or slowly and evenly cool it, to give the glass its durability and to prevent shattering or heat related breaking. At the end of the conveyor, workers carefully remove the cooled sheet of glass and cut it to the appropriate size.

Poker Faces by Peter McGrain

Sample Sets!

No matter if you are using our glass for architectural purposes or for hot glass applications (COE 90 and COE 96), we recommend you order some glass samples. Please visit: www.wissmachglass.com and you will find an order form for our sample packs under "Resources"

18



Stay Connected

The Paul Wissmach Glass Co. Inc.

420 Stephen St. Paden City, WV 26159 - USA

Telephone: (304) 337-2253 Fax: (304) 337-8800

wissmach@frontier.com

www.wissmachglass.com

Wissmachglass.com





